



1014 Grit-o'Cob®

DERIVED FROM THE WOODY PORTION OF THE CORN COB

PARTICLE SIZE DISTRIBUTION - SCREEN ANALYSIS

U.S. Standard Mesh			Delphi	Mt. Pulaski	Minimum	Maximum
Pass	Retained		Typical %	Typical %	%	%
-	10		1	1	0	2
10	14		70	86		
14	20		15	14		
20	30		5	1		
30	40		1	1		
40	-40		0.9	0.9	0	1

SUMMARY OF PHYSICAL PROPERTIES

Moisture, maximum %		10	Resistance to attrition, %	>98.6
Delphi	Bulk density, lb/ft ³	27 - 35		
Mt. Pulaski	Bulk density, lb/ft ³	27 - 35		

This information was derived from analytical and experimental data generated by The Andersons and supplemented by data obtained from manufacturers using various corn cob products in a variety of applications. For properties not listed and specific to your use, contact The Andersons Corn Cob Products.

Revised April 2013D/MP

Grit-o'Cob is a registered trademark of The Andersons.